

Zirconium Sponge

Table 1. Chemistry (ppm)

Standard Size	Industry Grade +20 Mesh	702 ASTM B494 -3/4" +20 Mesh	Alloy Grade Rotate 1% Hf Max -3/4" +3/8"	Reactor Grade ASTM B349 -1" +20 Mesh	Reactor Grade Rotate -3/4" +3/8"
BHN					
Zr + Hf MIN	95% MIN	99.2%	99.2%	99.5%	99.55%
C	500	500	300	250	250
O	3000		900	1400	800
N	3000	250	80	50	50
Cl	1500		500	1300	400
Mg	1000	600	600		
Al	500		500	75	75
B			10	0.5	0.5
Bi			50		50
Cd			35	0.5	
Co				20	
Cu			100	30	30
Cr	1000		400	200	100
Fe	10000		2000	1500	600
Hf		4.5%	10000	100	100
H		50	50		
Mn			100	50	50
Mo			100	50	50
Na			100		50
Nb	500		500		100
Ni	500		200	70	50
P			100		50
Pb			100		100
S			20		20
Si	500		150	120	100
Sn	500		500		200
Ta			200		200
Ti	1000		200	50	50
W			500	50	40
U				3	
Fe+ Cr		2000			

SIZES

- 1" +20 Mesh
- 3/4" +20 Mesh
- 3/8" +20 Mesh
- 12 Mesh +20 Mesh

Table 2. QUANTITY INCREMENT		
50-99 100-199 200-499	500-999 1,000-1,999 2,000-4,999	5,000-9,999 10,000-20,000 >20,000 Negotiable
50 lbs minimum order required.		

Table 3. STANDARD PACKAGING			
Order Size	Drum Size	Max Lbs/Drum	Shipment mode
800 lbs	55 Gal	800 lbs net	Truck/Ship
350 lbs	30 Gal	350 lbs net	Truck/Ship
50 lbs	5 Gal	50 lbs net	Truck/Ship
50 lbs		Gross	Air